

IN THE SPECIFICATION:

Please amend the Specification as follows.

Page 5, paragraph beginning on line 6:

The bonding consisting of silver brazing is carried out by abutting a disk (having a thickness of 50 μm) made of the silver brazing material to a corresponding end surface of the shaft 3a of the turbine 3, and a disk (having a thickness of 500 μm) made of Koval on the outer end surface of the silver brazing material. The end surface of the shaft 3a may have a surface roughness in the range of 0.8s to 3.2s, and the end surfaces of the Koval disk may have a surface roughness in the range of 3.2s to 25s.

Page 7, paragraph beginning on line 16:

The permanent magnet 2 preferably consists of a one-piece member, but may also consist of a plurality of pieces separated by planes vertical to or parallel with the axial line.